



PATENT NO. 8229-018-27 CIP			
<b><u>IN THE UNITED STATES PATENT AND TRADEMARK OFFICE</u></b>			
IN RE APPLICATION OF:	JAMES A. HUNTER, ET AL.	ART UNIT:	2872
SERIAL NO.:	10/050,994	EXAMINER:	AMARI, A.
FILING DATE: JANUARY 22, 2002			
FOR: HIGH CONTRAST GRATING LIGHT VALVE			
<b><u>REQUEST FOR RECONSIDERATION</u></b>			
ASSISTANT COMMISSIONER FOR PATENTS PO BOX 1450 ALEXANDRIA, VA 22313-1450			
SIR:			

Responsive to the Final Office Action issued in the above-captioned patent application on September 29, 2004, and in light of the Request for Continued Examination submitted herewith, withdrawal of the rejection of all claims as anticipated or obvious over U.S. Patent 6,233,087, Hawkins, alone or in view of U.S. Patent 5,311,360, Bloom, is respectfully requested.

Specifically, Applicants have previously presented, in the form of Declarations responsive to the rejection over U.S. Patent, 6,169,624, now withdrawn, evidence tending to demonstrate a date of invention of the subject matter claimed in advance of the effective filing dates of both the '624 and '087 patents. Those respective filing dates are August 11, 1999 and December 18, 1998.

In the Office Action of September 2004, the rejection over U.S. Patent 6,233,087, only, alone or in view of the '360 patent, was maintained, it being the position of the Examiner that none of the exhibits provided in the Declaration provide any test results to show that the subject

matter claimed worked for the intended purpose. The Examiner also questions, pages 2-5 of the Outstanding Office Action, whether the exhibits submitted demonstrate all the elements of the claims.

Applicants rely on the evidence originally submitted, together with the Declaration of Hunter submitted herewith. Time has not allowed the preparation of an executed Declaration, but Applicants submit the unexecuted Declaration herewith, and will submit an executed version of the same shortly. This Declaration of Hunter under 37 C.F.R. §1.131 demonstrates that in fact the subject matter of the invention was made prior to the effective filing dates of the references by the inventors. Accordingly, withdrawal of the rejections for anticipation and obviousness is respectfully requested.

Respectfully submitted,


MERCHANT & GOULD



Steven B. Kelber  
Registration No. 30,073  
Attorney of Record

901 Fifteenth Street, N.W.  
Suite 850  
Washington, DC 20005  
Telephone: (202) 326-0428  
Facsimile: (202) 326-0778





DOCKET NO. 8229-018-27 CIP

**IN THE UNITED STATES PATENT AND TRADEMARK OFFICE**

IN RE APPLICATION OF:	JAMES A. HUNTER, ET AL.	ART UNIT:	2872
SERIAL NO.:	10/050,994	EXAMINER:	AMARI, A.
FILING DATE: JANUARY 22, 2002			
FOR: HIGH CONTRAST GRATING LIGHT VALVE			

**DECLARATION OF JAMES A. HUNTER**

ASSISTANT COMMISSIONER FOR PATENTS  
PO BOX 1450  
ALEXANDRIA, VA 22313-1450

SIR:

I, James A. Hunter, do hereby declare and state that:

1. I am a co-inventor of the subject matter claimed in the above-captioned patent application.
2. It is my understanding that one claim of the above-captioned patent application is directed to a reflective light processing element, which may be a grating light valve.
3. I further understand that the grating light valve of the invention includes, as separate elements, a substrate, a dielectric layer formed on the substrate, a conductive trace formed on the dielectric layer and a plurality of ribbons formed above the substrate and the conductive trace. The conductive trace allows charges trapped in the dielectric layer to escape.
4. I am informed that there is no specific purpose recited for this grating light valve, no

specific function, but it is my general understanding, and was prior to December 1989, that a grating light valve is shown to work for its intended purpose when it is demonstrated that it can alter reflective light by movement from conditions of constructive to destructive interference. Specially, a grating light valve, or other light processing element, is shown to work when it modulates the amount of light reflected.

5. Submitted herewith as Exhibit A is a document that was employed at Silicon Light Machines prior to December 1989, referred to as a "runsheets." A runsheet identifies all processes that an actual product is subjected to. The runsheet that is Exhibit A is a runsheet for the preparation of the reflective light processing element having the features described above for the claimed invention of the above-captioned patent application. Exhibit B hereto is a spreadsheet prepared by me, that identifies the correlation between specific steps of the runsheet and a feature of the subject matter referred to above. Claim 1 also corresponds to Claim 1 of the above-captioned patent application.
6. The runsheet that is Exhibit A corresponds to the actual preparation of a prototype of the invention of Claim 1. As it was not a commercial run, nor prepared for a customer, many of the specific details, such as lot number and the like, were not incorporated. As set forth in Exhibit B, certain steps of the run sheet correspond to specific elements or recitations of Claim 1. Each of these is discussed below.
7. Thus, in steps 1 and 2, the runsheet begins with a silicon wafer, which corresponds to the "substrate" of Claim 1. In Step 2 a dry oxidation proceeds on the wafer, which forms an insulating dielectric (silicon dioxide) which corresponds to the recitation of Claim 1 that there be a "dielectric layer formed on the substrate."
8. In step 8 there is reference to deposition of ribbon material, followed in step 9 by the

patterning (ribbon mask) to form "a plurality of ribbons" as required in Claim 1, which is specifically recited in step 11, a step described as the ribbon etch. Thus, an 850 angstroms silicon nitride and 500 angstroms silicon dioxide etch is performed, resulted in a plurality of ribbons, as indicated on the runsheet.

9. At runsheet step 17, the step referred to as a partial release, exposes the dielectric on the substrate without releasing the ribbons fully. This is for the purpose of forming a conductive trace on the dielectric layer. The contact mask of step 18 is a mask for forming the contact for a conductive trace on the dielectric layer.
10. Step 20 of the runsheet is a contact etch step, that is, etching a contact hole for the conductive metal trace formed on the dielectric layer which is formed in Step 21 of the runsheet, metal evaporation. Thereafter, the device comprises the substrate formed at the beginning, step 1, with a dielectric layer thereon, step 2. There is a plurality of ribbons with material deposited, masked and etched in steps 8, 9, and 11 with a conductive trace and contact for the conductive trace formed in steps 17, 18, 20, 21 and 22. Step 23 is a "final release" which releases the ribbons so as to permit movement from constructive to destructive interference conditions.
11. As can be seen, accordingly, by performing the process set forth in the runsheet as was done at Silicon Light Machines by me and individuals working with me and under my direction, the subject matter of Claim 1 can be produced and was produced at Silicon Light Machines prior to December 1989. Moreover, as tested to the satisfaction of myself and my co-inventors, these grating light valves were shown to modulate the amount of light reflected by them from a light source, thereby demonstrating that the grating light valves made prior to August 11, 1989, by myself and co-inventors, in fact "worked for the intended purpose" in that they showed utility

as grating light valves.

All statements made herein are of my own knowledge are true and all statements made on information and belief are believed true. Further, I am aware that willful false statements and the like are punishable by fine, imprisonment, or both, 18 USC 1001, and that such willful false statements may jeopardize the validity of U.S. Patent Application 10/029,875 and any patent to issue thereon.

Date \_\_\_\_\_

\_\_\_\_\_  
James A. Hunter

# **EXHIBIT A**

\_\_\_\_\_ *Runsheets*

Lot Number:

STEP #	STEP	PROCESS	INIT	DATE												
1	WAFER START	<p>START P+ SUBSTRATES</p> <p>Prime ____-type &lt;____&gt; Silicon Vendor _____</p> <p>Resistivity: _____ ohm-cm; Lot #: _____</p>	_____	_____												
2	DRY OXIDATION	<p>Scribe wafers Scribe ID: <u>Lot ID ?</u></p> <p>Post Scribe Clean (wbnonmetal) 10 minutes Piranha</p> <p>Pre Diffusion Clean (wbdiff) 10 minutes Piranha 30 seconds 50:1 HF 10 minutes HCL/H<sub>2</sub>O<sub>2</sub>/H<sub>2</sub>O</p> <p>950° C Dry Oxidation - Target <u>500</u> Å (Tylan 1,3,4) Recipe: DRY950 Oxidation time: _____ minutes Furnace: tytan _____</p> <p>Measure:</p> <table> <tr> <td></td><td><u>Flat</u></td><td><u>Center</u></td><td><u>Top</u></td></tr> <tr> <td>Door:</td><td>_____</td><td>_____</td><td>_____ Å</td></tr> <tr> <td>Jungle:</td><td>_____</td><td>_____</td><td>_____ Å</td></tr> </table>		<u>Flat</u>	<u>Center</u>	<u>Top</u>	Door:	_____	_____	_____ Å	Jungle:	_____	_____	_____ Å	<p>_____</p> <p>_____</p> <p>_____</p> <p>_____</p>	<p>_____ ←</p> <p>_____ ←</p> <p>_____ ←</p> <p>_____ ←</p>
	<u>Flat</u>	<u>Center</u>	<u>Top</u>													
Door:	_____	_____	_____ Å													
Jungle:	_____	_____	_____ Å													



STEP #	STEP	PROCESS	INIT	DATE																
3	AMORPHOUS SILICON DEP	<p>Pre Clean (w/metal)</p> <p>6 cycle dump rinse</p> <p>Add 3 1000 Å oxide test wafers source?</p> <p>550° C amorphous silicon deposition</p> <p>Target 8700Å ? redo?</p> <p>Recipe: _____</p> <p>Furnace: TYSTAR1</p> <p>Deposition rate from test run: _____ Å/min</p> <p>Deposition time: _____ minutes</p> <p>Measure (thickness):</p> <table><tr><td></td><td>Flat</td><td>Center</td><td>Top</td></tr><tr><td>Door:</td><td>_____</td><td>_____</td><td>_____ Å</td></tr><tr><td>Center:</td><td>_____</td><td>_____</td><td>_____ Å</td></tr><tr><td>Jungle:</td><td>_____</td><td>_____</td><td>_____ Å</td></tr></table>		Flat	Center	Top	Door:	_____	_____	_____ Å	Center:	_____	_____	_____ Å	Jungle:	_____	_____	_____ Å	<p>_____</p> <p>_____</p> <p>_____</p> <p>_____</p> <p>_____</p> <p>_____</p>	<p>_____</p> <p>←</p> <p>_____</p> <p>←</p> <p>_____</p> <p>_____</p>
	Flat	Center	Top																	
Door:	_____	_____	_____ Å																	
Center:	_____	_____	_____ Å																	
Jungle:	_____	_____	_____ Å																	
4	POST MASK	<p>_____ Mask: Level _____ Rev _____</p> <p>Singe (singe oven) 20 minutes 150° C</p> <p>Spin Resist (svgcoat)</p> <p>Prime, Spin and Prebake Program 1 (run Program 10 to prime lines)</p>	<p>_____</p> <p>_____</p> <p>_____</p> <p>_____</p>	<p>_____</p> <p>←</p> <p>_____</p> <p>_____</p>																

STEP #	STEP	PROCESS	INIT	DATE
		Expose <i>(ultratech)</i> Reticle = _____, Field = _____  Exposure: _____  Focus Offset: _____  Develop/Inspect <i>(svgdev)</i> Develop and Postbake Program 1  Wafer #: _____  Verniers: _____  Dagger: _____  Lines: _____  Corners: _____	_____	_____
5	DESCUM	Descum <i>(drytek2)</i> Recipe: descum 2.5 minute etch	_____	_____
6	POST ETCH	Etch _____ <i>(drytek2)</i> Recipe: _____ Etch Time: _____ minutes	_____	_____

STEP #	STEP	PROCESS	INIT	DATE
		Final Inspect (same wafer from photo):  Wafer #: _____  Verniers: _____  Dagger: _____  Lines: _____  Corners: _____	_____	_____
7	PIRANHA RESIST STRIP	Strip Resist (wet) (wbnonmetal) 20 minutes Piranha 10 minutes Piranha	_____	_____
8	STRATA- GLASS THERMAL NITRIDE DEPOSITION	Outside Services: <u>Strataglass</u> <i>why?</i> Call courier for pickup (Add 2-3 pre-stress test wafers)  LPCVD Nitride: Target <u>850</u> Å DCS:NH <sub>3</sub> Ratio: _____  Measure (RI):  <div style="text-align: center;"> <u>Flat</u>      <u>Center</u>      <u>Top</u> </div> Door:      _____      _____      _____ Å  Center:      _____      _____      _____ Å  Jungle:      _____      _____      _____ Å	← _____  _____  _____	_____  _____  _____

STEP #	STEP	PROCESS	INIT	DATE
		Measure (thickness):  <div> <u>Flat</u>      <u>Center</u>      <u>Top</u> </div> Door:      _____      _____      _____ Å Center:      _____      _____      _____ Å Jungle:      _____      _____      _____ Å  Measure (stress):  Door:      _____ MPa Center:      _____ MPa Jungle:      _____ MPa	_____          _____	_____          _____
9	RIBBON MASK	_____ Mask: Level _____ Rev _____  Singe ( <i>singe oven</i> ) 20 minutes 150° C  Spin Resist ( <i>svgcoat</i> ) Prime, Spin and Prebake Program 1 (run Program 10 to prime lines)  Expose ( <i>ultratech</i> ) Reticle = _____, Field = _____	_____  _____  _____  _____	_____  _____  _____  _____

STEP #	STEP	PROCESS	INIT	DATE
		Exposure: _____  Focus Offset: _____    Develop/Inspect (svgdev) Develop and Postbake Program 1  Wafer #: _____  Verniers: _____  Dagger: _____  Lines: _____  Corners: _____	_____	_____
10	DESCUM	Descum (drytek2) Recipe: descum 2.5 minute etch	_____	_____
11	RIBBON ETCH	Etch _____ (amtetcher) Recipe: _____ Etch Time: _____ minutes  <i>etch 850 Å 51N and 500 Å 51OZ</i>	_____	_____

*Resist strip?*

STEP #	STEP	PROCESS	INIT	DATE
		Final Inspect (same wafer from photo):  Wafer #: _____  Verniers: _____  Dagger: _____  Lines: _____  Corners: _____	_____	_____
12	CIS METAL SPUTTER	Pre Clean <i>(wbmetal)</i> 30 seconds 50:1 HF  Metal Dep <i>(gryphon)</i> _____ Equivalent oxide etch _____ Sputter Deposition Target: <u>3000 Å</u>  Measure (Rs):  <u>Flat</u> <u>Center</u> <u>Top</u>  _____          _____          _____ ohm/sq	_____   _____   _____	_____   _____   _____
13	M2 MASK	_____ Mask: Level _____ Rev _____  Singe <i>(singe oven)</i> 20 minutes 150° C	_____  _____	_____  _____

STEP #	STEP	PROCESS	INIT	DATE
		Spin Resist <i>(svgcoat)</i> Prime, Spin and Prebake Program 1 (run Program 10 to prime lines)  Expose <i>(ultratech)</i> Reticle = _____, Field = _____  Exposure: _____  Focus Offset: _____  Develop/Inspect <i>(svgdev)</i> Develop and Postbake Program 1  Wafer #: _____  Verniers: _____  Dagger: _____  Lines: _____  Corners: _____	_____   _____   _____	_____   _____   _____
14	DESCUM	Descum <i>(drytek2)</i> Recipe: descum 2.5 minute etch	_____	_____
15	WET METAL ETCH	Pour fresh etchant Etchant: _____ <i>(wbmetal)</i>	_____	_____

STEP #	STEP	PROCESS	INIT	DATE
		Etch metal to clear Etch Time: _____ minutes	_____	_____
16	RESIST ASH	Strip Resist (dry) ( <i>matrix</i> ) Recipe: newlotemp Strip Time: _____ minutes  Post Clean 6 cycle Dump Rinse ( <i>wbmetal</i> )	_____	_____
17	PARTIAL RELEASE	WAFERS NEED TO GO TO SLM ← NOE? <i>clean?</i>		
18	CONTACT MASK	_____ Mask: Level _____ Rev _____  Singe ( <i>singe oven</i> ) 20 minutes 150° C  Spin Resist ( <i>svgcoat</i> ) Prime, Spin and Prebake Program 1 (run Program 10 to prime lines)	_____  _____  _____	_____  _____  _____



STEP #	STEP	PROCESS	INIT	DATE
		Expose <i>(ultratech)</i> Reticle = _____, Field = _____  Exposure: _____  Focus Offset: _____          Develop/Inspect <i>(svgdev)</i> Develop and Postbake Program 1  Wafer #: _____  Verniers: _____  Dagger: _____  Lines: _____  Corners: _____	_____          _____	_____          _____
19	DESCUM	Descum <i>(drytek2)</i> Recipe: descum 2.5 minute etch	_____	_____
20	CONTACT ETCH	Etch _____ <i>(amtetcher)</i> Recipe: _____ Etch Time: _____ minutes	_____	_____

STEP #	STEP	PROCESS	INIT	DATE
		Final Inspect (same wafer from photo):  Wafer #: _____  Verniers: _____  Dagger: _____  Lines: _____  Corners: _____	_____	_____
21	METAL EVAP	WAFERS NEED TO GO TO LANCE GODDARD	500 Å	
22	ALLOY	<i>simulate seal furnace?</i>		
23	FINAL RELEASE	WAFERS NEED TO GO TO SLM		

# **EXHIBIT B**

**RUNSH  
EET  
DETAIL  
ED  
DESCRI  
PTION**

Step #	Step Name	Comments	Claim Reference
1	WAFER START	Starting Si Substrate	Claim 1, "a substrate"
2	DRY OXIDATION	Grow an insulating dielectric	Claim 1, "a dielectric layer formed on the substrate"
3	AMORPHOUS SILICON DEP	Deposit Si sacrificial layer	NA
4	POST MASK	Photo patterning of ribbon anchor	NA
5	DESCUM	Ashing of residual photoresist	NA
6	POST ETCH	Forms ribbon anchor "mold"	NA
7	PIRANHA RESIST STRIP	Strips resist	NA
8	STRATAGLASS THERMAL NITRIDE DEPOSITION	Ribbon material deposition	Claim 1, "a plurality of ribbons..."
9	RIBBON MASK	Photo patterning of ribbon	Claim 1, "a plurality of ribbons..."
10	DESCUM	Ashing of residual photoresist	NA
11	RIBBON ETCH	Etching of ribbon	Claim 1, "a plurality of ribbons..."
12	CIS METAL SPUTTER	Deposition of thick metal wiring	NA
13	M2 MASK	Photo patterning of thick metal wiring	NA
14	DESCUM	Ashing of residual photoresist	NA
15	WET METAL ETCH	Etching of thick metal wiring	NA
16	RESIST ASH	Strips resist	NA
17	PARTIAL RELEASE	Exposes dielectric on substrate without releasing ribbons fully	Claim 1, "a conductive trace on the dielectric layer.."
18	CONTACT MASK	Photo patterning of contact hole for conductive metal trace	Claim 1, contact for "a conductive trace on the dielectric layer.."
19	DESCUM	Ashing of residual photoresist	NA
20	CONTACT ETCH	Etching of contact hole for conductive metal trace	Claim 1, contact for "a conductive trace on the dielectric layer.."
21	METAL EVAP	Formation of conductive trace	Claim 1, "a conductive trace on the dielectric layer.."
22	ALLOY	Sinters contact	Claim 1, contact for "a conductive trace on the dielectric layer.."
23	FINAL RELEASE	Fully releases ribbons	Claim 1, "a plurality of ribbons..."